



## **Mineral/Glass Filled Nylon 66 (Black)**

<b>Physical Properties</b>	<b>Test Method</b>	<b>Results</b>
Density	ASTM D792	1.45
Filler Content	Glass & Mineral	38%
<b>Mechanical Properties</b>		
Tensile Strength	ASTM D638	16,800 psi
Elongation at Break	ASTM D638	3%
Flexural Modulus	ASTM D790	1,000 psi
Flexural Strength	ASTM D790	26,500 psi
Izod Impact, Notched	ASTM D256	0.8 ft-lb/in

**Datasheet shows target properties for product**

Before using this product, the user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in question and is further advised against relying on the information contained herein as it may relate to any specific use or application. It is the ultimate responsibility of the user to ensure that the product is suited and the information is applicable to the user's specific application. Lone Star Chemical does not make, and expressly disclaims, all warranties, including warranties of merchant- ability or fitness for a particular purpose, regardless of whether oral or written, express or implied, or allegedly arising from any usage of any trade or from any course of dealing in connection with the use of the information contained herein or the product itself. The user expressly assumes all risk and liability, whether based in contract, tort or otherwise, in connection with the use of the information contained herein or the product itself. Further, in- formation contained herein is given without reverence to any intellectual property issues, as well as federal, state or local laws which may be encountered in the use thereof. Such questions should be investigated by the user.