



Product Datasheet

LSC-PPCO-20

Product Properties

Typical Properties	Method	Value Unit
Physical		
Melt Flow Rate (230 C/2.16kg)	ASTM D 1238	20.0 g/10 min
Density- Specific Gravity	ASTM D 1505	0.905 sp gr
Mechanical		
Tensile Strength @ Yield (2 in/min) (50 mm/min)	ASTM D 638	3600 PSI 24.8 MPa
Flexural Modulus (0.05 in/min, 1 % Secant, Procedure A) (1 mm/min, 1 % Secant, Procedure A)	ASTM D 790	195,000 PSI 1340 MPa
Tensile Elongation @yld	ASTM D 638	n/a
IMPACT		
Notched izod impact (73 F, Method A) (23 C, Method A)	ASTM D 256	2.2 ft-lb/in 117 J/m
Hardness		
Rockwell Hardness (R-Scale)	ASTM D 785	91
Thermal		
DTUL @66psi - Unannealed	ASTM D 648	107 C

Before using this product, the user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in question and is further advised against relying on the information contained herein as it may relate to any specific use or application. It is the ultimate responsibility of the user to ensure that the product is suited and the information is applicable to the user's specific application. Lone Star Chemical does not make, and expressly disclaims, all warranties, including warranties of merchant- ability or fitness for a particular purpose, regardless of whether oral or written, express or implied, or allegedly arising from any usage of any trade or from any course of dealing in connection with the use of the information contained herein or the product itself. The user expressly assumes all risk and liability, whether based in contract, tort or otherwise, in connection with the use of the information contained herein or the product itself. Further, in- formation contained herein is given without reverence to any intellectual property issues, as well as federal, state or local laws which may be encountered in the use thereof. Such questions should be investigated by the user.