

## StarPlas PPCR 350 CL

Random Clarified Copolymer PP Clarified, Injection Molding grade, FDA

Melt Flow	ASTM Test	Typical Value	
Flow, gm/10 min.,	D-1238	35.0	StarPlas PPCR 350 CL is a clarified
230/2.16			random copolymer with great clarity.
			StarPlas PPCR 350 CL is an injection
Impact Properties	ASTM Test	Typical Value	molded grade used for parts that need
			high clarity with decent impact.
Izod, ft-lbs/in, notched	D-256	1.4	
			Please contact us with any additional
<b>Tensile Properties</b>	ASTM Test	Typical Value	questions you may have regarding this
			material. (940) 381-2000
Strength, psi	D-638	4,000	material. (540) 301 2000
Elongation, %	D-638	14	
Flexural Properties	ASTM Test	Typical Value	
Modulus, psi	D-790	150,000	
Thermal Properties	ASTM Test	Typical Value	
Heat Distortion, F	D-648	180	
Annealed			

## **Other Information**

This material will comply with FDA requirements as described in 21 CFR 177.1640.

The above values are intended as a general guide and do not represent results that may be obtained elsewhere. Lone Star Chemical makes no warranty of merchantability and there is no warranty that goods supplied shall be fit for any particular purpose.

