

Technical Data Sheet Polypropylene – Homopolymer Produced in the United States

TotalEnergies Petrochemicals & Refining USA, Inc. Polymers Americas

## **Description**

Polypropylene 3273 utilizes proprietary process technology to provide low residuals for improved film stiffness and barrier properties.

**FDA:** 3273 complies with applicable FDA regulations for use in food contact applications. FDA statement available upon request.

Applications: 3273 is recommended in orientation processes for manufacture of packaging tapes and films.

**Processing:** 3273 resin processes on oriented film extrusion equipment with typical melt temperatures of 450°F-525°F (232°C-274°C).

## **Characteristics**

	Method	Unit	Typical Value
Rheological Properties			
Melt Flow	D-1238	g/10 min	2.0
Film Properties, Oriented (1)(3)			
Haze	D-1003	%	1.0
Gloss, 45°	D-2457	%	85
Elongation	D-882	% MD (TD)	150 (60)
Ultimate Tensile	D-882	psi MD (TD)	24,000 (38,000)
Tensile Modulus	D-882	psi MD (TD)	400,000 (686,000)
WVTR @ 100°F, 90% RH	F-1249-90	g • mil /100 in²/24 hr	0.25
Thermal Properties <sup>(1)(2)</sup>			
Melting Point	DSC	°F (°C)	325 (163)
Other Physical Properties			
Density	D-1505	g/cc	0.905

<sup>(1)</sup> Data developed under laboratory conditions and are not to be used as specification, maxima or minima.

(3) Tenter-frame oriented film.

Rev: Aug 2023

<sup>(2)</sup> MP determined with a DSC-2 Differential Scanning Calorimeter. Test procedure available upon request.