

Technical Data Sheet Polypropylene – Homopolymer Produced in the United States

TotalEnergies Petrochemicals & Refining USA, Inc. Polymers Americas

## **Description**

Polypropylene 3860X features extremely high purity for processing in micro denier fibers.

FDA: 3860X complies with all applicable FDA regulations for food contact applications.

**Applications:** 3860X is recommended for nonwoven fiber applications.

**Processing:** 3860X processes on conventional extrusion equipment with typical melt temperatures of 450°F-550°F (232°C-288°C).

## **Characteristics**

	Method	Unit	Typical Value
Rheological Properties	1		<u>'</u>
Melt Flow	D-1238	g/10 min	100
Mechanical Properties			
Tensile Modulus	D-638	psi (MPa)	240,000 (1,655)
Flexural Modulus	D-790	psi (MPa)	229,000 (1,580)
Thermal Properties <sup>(1)(2)</sup>			
Melting Point	DSC	°F (°C)	330 (165)
Other Physical Properties			
Density	D-1505	g/cc	0.905

<sup>(1)</sup> Data developed under laboratory conditions and are not to be used as specification, maxima or minima.

Rev: Sept 2021

TOTALENERGIES PETROCHEMICALS & REFINING USA, INC. POLYMERS AMERICAS
1201 Louisiana Street
Suite 1800
Houston, TX 77002
www.polymers.totalenergies.com

TECHNICAL CENTER P.O. Box 1200 Deer Park, Texas 77536 Phone: 281-884-7500

1-800-344-3462

<sup>(2)</sup> MP determined with a DSC-2 Differential Scanning Calorimeter. Test procedure available upon request.