

TotalEnergies Petrochemicals & Refining USA, Inc.  
Polymers Americas

## Description

**Polypropylene 6575:** Low catalyst residuals results in improved color stability.

**Clarity/Impact:** 6575 improves its clarity and resiliency over conventional homopolymer films.

**FDA:** 6575 complies with all applicable FDA regulations for food contact applications.

**Recommended Applications:** 6575 is recommended for use in manufacture of packaging films that require improved optical and resiliency or special surface attributes.

**Processing:** 6575 resin processes with typical melt temperatures of 450°F-525°F (232°C-274°C).

## Characteristics

	Method	Unit	Typical Value
<b>Rheological Properties</b>			
Melt Flow	D-1238	g/10 min	8.0
<b>Film Properties, Non-Oriented<sup>(1)(3)</sup></b>			
Ultimate Tensile	D-882	psi (MPa)	7,000 (48)
Elongation at Break	D-882	%	500
1% Secant Modulus	D-882	psi (MPa)	100,000 (689)
WVTR @ 100°F, 90% RH	F-1249-90	g/100 sq-in/24 hrs/mil	0.7
Haze	D-1003	%	2.0
Gloss@ 45°	D-2457	%	80
Dart Impact (F50)	D-1709	g/mil	35
<b>Thermal Properties<sup>(1)(2)</sup></b>			
Melting Point	DSC	°F (°C)	293 (145)
<b>Other Physical Properties</b>			
Density	D-792	g/cc	0.90

- (1) Data developed under laboratory conditions and are not to be used as specification, maxima or minima.  
 (2) MP determined with a DSC-2 Differential Scanning Calorimeter. Test procedure available upon request.  
 (3) Cast film, 2.0 mil

Rev: May 2022

TOTALENERGIES PETROCHEMICALS & REFINING USA, INC.  
POLYMERS AMERICAS  
1201 Louisiana Street  
Suite 1800  
Houston, TX 77002  
[www.polymers.totalenergies.com](http://www.polymers.totalenergies.com)

TECHNICAL CENTER  
P.O. Box 1200  
Deer Park, Texas 77536  
Phone: 281-884-7500

**1-800-344-3462**