



TotalEnergies

TotalEnergies Petrochemicals & Refining USA, Inc.
Polymers Americas

Lumicene® Polypropylene M8825KZ

Technical Data Sheet
Metallocene Polypropylene – Random Copolymer
Produced in the United States

Description

Clarity – M8825KZ exhibits excellent clarity in molded parts.

Impact – M8825KZ produces molded parts with improved impact in comparison to parts molded from conventional clarified random copolymers.

Antistat – M8825KZ contains an antistat to help protect molded parts from dust accumulation.

FDA – M8825KZ complies with all applicable FDA regulations for food contact applications.

Applications – M8825KZ is recommended for injection molding housewares, caps and closures, packaging and other items requiring a balance of impact, clarity and easy mold release.

Processing – M8825KZ resin processes on conventional injection molding equipment with typical melt temperatures of 390°F-450°F (200°C-232°C).

Characteristics

	Method	Unit	Typical Value
Rheological Properties			
Melt Flow	D-1238	g/10 min	30
Mechanical Properties⁽¹⁾			
Tensile Modulus	D-638	psi (MPa)	180,000 (1,240)
Elongation	D-638	%	12
Flexural Modulus	D-780	psi (MPa)	173,000 (1,195)
Izod Impact @ 73 °F, Notched	D-256A	ft.lb/in (J/m)	0.7 (37)
Haze, 0.04" plaques	D-1003	%	8
Thermal Properties⁽¹⁾⁽²⁾			
Melting Point	DSC	°F (°C)	277 (136)
Heat Deflection @ 66 Psi	D-648	°F	192
@ 4.64 kg/cm ²		°C	89
Other Physical Properties			
Density	D-1505	g/cc	0.9

(1) Data developed under laboratory conditions and are not to be used as specification, maxima or minima.
(2) MP determined with a DSC-2 Differential Scanning Calorimeter. Test procedure available upon request.

Rev: Sept 2021

TOTALENERGIES PETROCHEMICALS & REFINING USA, INC.
POLYMERS AMERICAS
1201 Louisiana Street
Suite 1800
Houston, TX 77002
www.polymers.totalenergies.com

TECHNICAL CENTER
P.O. Box 1200
Deer Park, Texas 77536
Phone: 281-884-7500

1-800-344-3462

Polypropylene